

## DATASHEET – POM-C

**DELRIN®, ERTACETAL®, ZELLAMID®,  
HOSTAFORM®, SUSTARIN®, ULTRAFORM®**

### KEY POINTS

- High strength and stiffness
- Low friction
- High dimensional stability
- Electrical Insulation
- Low water absorption

### PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE	UNIT
Tensile strength (23°C)	ISO 527-1/-2	50-70	MPa
Elongation at break	ISO 527-1/-2	30-60	%
Hardness – Shore D	DIN 53505	81-85	Scale D
Hardness – Rockwell M	ISO 2039-2	125	MPa
Impact strength, notched izod	ISO 179-1/1eA	150	kJ/m <sup>2</sup>
Melt temp	ISO 11357-1/-3	165	°C
Service temp. range	/	-40 up to 100	°C
Specific density	ISO 1183-1	1.41	g/cm <sup>3</sup>
Water absorption (24hr)	ISO 62	< 0.15	%

### APPLICATIONS

- Gear wheels
- Bearings
- Fasteners
- Automotive components
- Pump components
- Food industry
- ...



Industrieterrein Zwaarveld 65  
B-9220 Hamme - Belgium

The data above are provided purely for information and are presented as a guide to choose from our range of materials. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. The actual values of the properties of a particular product may differ from the indicated values. Since the properties also depend on the dimension of the finished product.