

DuPont™ Vespel® SCP-5050

Polyimide Shapes

Typical Properties

DuPont™ Vespel® SCP-5050 parts and shapes improve high temperature performance and wear resistance to allow for the replacement of metal and graphite parts. Vespel® SCP-5050 parts and shapes enable more efficient and durable systems, increased performance and reduced maintenance costs. SCP-5050 has a Coefficient of Thermal Expansion (CTE) similar to steel.

Some data presented below are based on limited production runs and are subject to revision as new knowledge and experience become available.

Mechanical Properties	Temperature	Test Method	Units	Typical Values
Tensile Strength	23 °C (73 °F) 260 °C (500 °F)	ASTM D-638 D-1708 Specimen	MPa (kpsi)	72 (10.5) 38 (5.6)
Tensile Elongation	23 °C (73 °F) 260 °C (500 °F)	ASTM D-638 D-1708 Specimen	%	2.5 5.3
Young's Modulus	23 °C (73 °F) 260 °C (500 °F)	ASTM D-638 D-1708 Specimen	MPa (kpsi)	8,928 (1,295) 2,931 (425)
Flexural Strength	23 °C (73 °F) 260 °C (500 °F)	ASTM D-790	MPa (kpsi)	130 (19) 73 (11)
Flexural Modulus	23 °C (73 °F) 260 °C (500 °F)	ASTM D-790	MPa (kpsi)	7,800 (1,130) 5,080 (740)
Compressive Strength	23 °C (73 °F) 260 °C (500 °F)	ASTM D-695	MPa (kpsi)	219 (32) 240 (35)
Compressive Modulus	23 °C (73 °F) 260 °C (500 °F)	ASTM D-695	MPa (kpsi)	2,997 (435) 3,138 (455)
Compressive Stress at 10% Strain	23 °C (73 °F) 260 °C (500 °F)	ASTM D-695	MPa (kpsi)	172 (25.0) 184 (26.7)
Rockwell "E" Hardness	—	ASTM D-785	—	63
Deformation Under Load 24 hr, 14 MPa (2 kpsi)	23 °C (73 °F)	ASTM D-621	% deformation	0.03
Thermal Properties				
Coefficient of Thermal Expansion*	23 °C–300 °C (73 °F–572 °F)	ASTM E-831	m/m·°C or m/m·K (in/in·°F)	29 x 10 ⁻⁶ (16 x 10 ⁻⁶)
Specific Heat	60 °C (140 °F)	ASTM E-1269	J/kg °C (Btu/lb °F)	920 (0.22)
Other Properties				
Specific Gravity	—	ASTM D-792	—	1.76
Water Absorption after 24 hr	23 °C (73 °F)	ASTM D-570	% weight change	0.04

*Plaque CTE is 45 x 10⁻⁶ m/m·°C (25 x 10⁻⁶ in/in·°F) in the z direction and 16 x 10⁻⁶ m/m·°C (9 x 10⁻⁶ in/in·°F) in the x, y plane.



The miracles of science™

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2011 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez® and Vespel® are trademarks or registered trademarks of E. I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(07/09) Reference No. VPE-A10986-00-A0711 Previous Reference No. K-21996



The miracles of science™